

Historic, archived document


Do not assume content reflects current
scientific knowledge, policies, or practices

1.8
Ex 892E

LIBRARY
RECEIVED
MAR 15 1926
U. S. Department of Agriculture




SOME GRADES OF WOOL



4147-C

STRICTLY COMBING WOOL


Fine and long. (Natural size.) Equivalent to 64s U. S. Standards



422-D

CLOTHING WOOL

Fine and short. (Natural size.) Equivalent to 64s U. S. Standards



4145-C

BRAID WOOL

Coarse. (Natural size.) Equivalent to 36s and 40s U. S. Standards



4143-C

STRICTLY COMBING WOOL

Medium and long. (Natural size.) Equivalent to 48s U. S. Standards



33648-B

CLOTHING WOOL

Medium and short. (Natural size.) Equivalent to 48s U. S. Standards

Strictly combing, fine wool, is used for fine worsteds, very fine serges, challis, and lansdowns.
Clothing, fine wool, is used for fine woolens, broadcloth, underwear, and flannels.
Strictly combing, medium wool, is used for medium serges and worsted goods.
Clothing, medium wool, is used for coarse woolens and blankets.
Braid wool is used for homespuns, carpets, and plushes.

Division of Agricultural Instruction, Office of Cooperative Extension Work, Extension Service, in cooperation with the Bureaus of Animal Industry and Agricultural Economics, United States Department of Agriculture, Washington, D. C.